

We claim:

1. A mixture comprising

5

A) at least one copolymer obtainable by

(i) free-radically initiated solution polymerization of a
monomer mixture of

10

(a) 0.01 to 99.99% by weight of at least one monomer
chosen from the group consisting of N-vinylimidazoles
and diallylamines, optionally in partially or
completely quaternized form;

15

(b) 0.01 to 99.99% by weight of at least one neutral or
basic water-soluble monomer which is different from
(a);

20

(c) 0 to 50% by weight of at least one unsaturated acid
or an unsaturated anhydride;

25

(d) 0 to 50% by weight of at least one free-radically
copolymerizable monomer which is different from (a),
(b) and (c); and

30

(e) 0 to 10% by weight of at least one monomer having at
least two ethylenically unsaturated nonconjugated
double bonds which acts as crosslinker, and

(ii) subsequent partial or complete quaternization or
protonation of the polymer where the monomer (a) is not
quaternized or only partially quaternized

35

and

B) at least one inorganic UV filter.

2. A mixture as claimed in claim 1, wherein the copolymer A) is
obtainable by solution polymerization in water.

40


3. A mixture as claimed in either of claims 1 and 2, wherein the
monomer (e) used is 0.01 to 10% by weight of at least one
monomer having at least two ethylenically unsaturated
nonconjugated double bonds which acts as crosslinker.

45

30


4. A mixture as claimed in any of claims 1 to 3, wherein the protonation according to (ii) takes place during the preparation of the mixture.
- 5 5. A mixture as claimed in any of claims 1 to 4, wherein the monomer (a) used is at least one N-vinylimidazole derivative of the formula (I)

10



- 15 in which the radicals R¹ to R³, independently of one another, are hydrogen, C₁-C₄-alkyl or phenyl.
6. A mixture as claimed in any of claims 1 to 4, wherein the monomer (a) used is at least one diallylamine derivative of the formula (II)
- 20


25



- 30 in which the radical R⁴ is C₁-C₂₄-alkyl.

7. A mixture as claimed in any of claims 1 to 6, wherein the monomer (b) used is at least one N-vinyl lactam.
8. A mixture as claimed in any of claims 1 to 7, comprising, as inorganic UV filter B), at least one micronized metal oxide chosen from the group consisting of titanium dioxide, zinc oxide, cerium oxide, aluminum oxide, silicon oxide, zirconium oxide, manganese oxide, aluminum oxide and iron oxide.
- 35
9. A mixture as claimed in claim 8, comprising, as inorganic UV filter B), at least one hydrophobicized metal oxide chosen from the group consisting of titanium dioxide and zinc oxide.
- 40
10. A mixture as claimed in claim 9, in which the metal oxide has been coated with a silicone of the formula III
- 45

31



- 5
- in which, independently of one another, R^5 is $\text{C}_1\text{-C}_{12}$ -alkyl and R^6 is methyl or ethyl, and a is a value from 4 to 12.
- 10
11. A mixture as claimed in any of claims 1 to 10, wherein the proportion of inorganic UV filters is 0.1 to 99.9% by weight.
12. A mixture as claimed in any of claims 1 to 11, comprising at least one further organic UVA and/or UVB filter.
- 15
13. The use of a mixture defined as in any of Claims 1 to 12 for the preparation of cosmetic and dermatological preparations.
14. The use as claimed in claim 13 as photostable UV filter in cosmetic and dermatological preparations for protecting the human skin or human hair against solar rays, alone or
- 20
- together with compounds which absorb in the UV region and which are known per se for cosmetic and pharmaceutical preparations.
- 25
15. A cosmetic or dermatological sunscreen preparation for protecting the human skin or human hair against solar rays, comprising a mixture defined as in any of claims 1 to 12.

30

35

40

45